



Mapecem 202[®]

Medium-Build, Two-Component, Fast-Setting Mortar



DESCRIPTION

Mapecem 202 is a two-component, shrinkage-compensated, polymer-modified, fast-setting cementitious mortar with a corrosion inhibitor.

FEATURES AND BENEFITS

- For concrete repair and topping applications from 1/4" to 2" (6 mm to 5 cm), or extended up to 20% by weight for thicknesses from 2" to 6" (5 to 15 cm) with 3/8" (10 mm) thoroughly washed, sound, saturated surface-dry (SSD) pea gravel
- Requires only the addition of its liquid (Part B), and is prepackaged with both components for easy field use and control
- Can be applied using a trowel or screed
- *Mapecem 202* can be opened to foot and rubber-wheel traffic within 4 hours.

INDUSTRY STANDARDS AND APPROVALS

LEED v4 Points Contribution

LEED Points

Health Product Declaration (HPD)*Up to 2 points

* Using this product may help contribute to LEED certification of projects in the category shown above. Points are awarded based on contributions of all project materials.

WHERE TO USE

- For horizontal, exterior/interior structural concrete repairs and toppings at thicknesses from 1/4" to 2" (6 mm to 5 cm)
- For use as a monolithic topping where fast drying is required

- When properly mixed and installed, *Mapecem 202* has a residual moisture content of less than 2.5% at 24 hours, making it ideal for floor-covering applications in residential, commercial, institutional and industrial structures.

SURFACE PREPARATION

- Concrete surface must be clean and free of loose particles, efflorescence, paint, tars, grease, asphaltic materials, bond breakers, curing compounds, wax and any foreign substance.
- Mechanically profile clean, sound and stable concrete surfaces to obtain a concrete surface profile (CSP) equal to or greater than #5 per ICRI Guideline #310.2R-2013.
- Clean any exposed steel reinforcement and coat with *Mapefer™ 1K* or *Planibond® 3C* (see the respective Technical Data Sheet for details) to protect against corrosion.

MIXING

Before product use, take appropriate safety precautions. Refer to the Safety Data Sheet for details.

1. Into a clean mixing pail, pour 4/5 of the required amount of latex liquid (Part B).
2. Slowly add the Part A powder to the liquid while mixing, using a low-speed mixer (at 300 to 500 rpm).
3. Add as much of the remaining 1/5 of liquid as needed to achieve the desired consistency. Mix for up to 4 minutes, removing any unmixed powder and remix to a smooth, homogenous consistency.



PRODUCT APPLICATION

Read all installation instructions thoroughly before installation.

1. Before application, ensure that prepared concrete is SSD.
2. Apply with a trowel or a screed, with or without formwork (screed rail), on a horizontal surface.

CURING

- Cure with wet burlap or polyethylene sheet during the first 4 hours of curing. Alternately, apply a water-based curing compound conforming to ASTM C309.

CLEANUP

- Wash hands and tools promptly with water before the material hardens. Cured material must be mechanically removed.

LIMITATIONS

- Do not add other additives, water or cements to *Mapecem 202*.
- Do not use solvent-based curing compounds.
- Only use between 45°F and 95°F (7°C and 35°C). Note that cool, damp and humid conditions will slow the rate of hydration and will cause the mortar to retain a higher moisture content for a longer period of time.

Product Performance Properties

Laboratory Tests	Results
Compressive strength – ASTM C109 (CAN/CSA-A5)	
4 hours	> 2,200 psi (15,2 MPa)
1 day	> 3,100 psi (21,4 MPa)
7 days	> 4,950 psi (34,1 MPa)
28 days	> 6,150 psi (42,4 MPa)
Flexural strength – ASTM C348 (CAN/CSA-A23.2-8C)	
1 day	> 650 psi (4,48 MPa)
7 days	> 1,085 psi (7,48 MPa)
28 days	> 1,500 psi (10,3 MPa)
Modulus of elasticity – ASTM C469, 28 days	2.6 x 10 ⁶ psi (18,0 GPa)
Slant/shear bond strength – ASTM C882 (modified)	
1 day	> 1,100 psi (7,59 MPa)
7 days	> 1,300 psi (8,97 MPa)
28 days	> 1,450 psi (10 MPa)
Pull-off bond strength – ASTM C1583	Greater than concrete (rupture of concrete substrate)
Volume change – ASTM C157 (modified)	
28 days, dry-cured	-0.04%
28 days, wet-cured	+0.015%
Abrasion resistance – ASTM D4060, after 7 days	
Taber H22-500 g, 200 cycles	< 1,5 g
Freeze/thaw resistance – ASTM C666-A (CAN/CSA A23.2-9B), 300 cycles	100%
Resistance to de-icing salts – ASTM C672 (CAN/CSA A23.2-16C), 50 cycles	0 rating, no scaling
Permeability to chlorides – ASTM C1202 (AASHTO T277), 28 days	Very low – in the range of 100 to 1,000 coulombs
VOCs (Rule #1168 of California's SCAQMD)	0 g per L

Shelf Life and Product Characteristics (before mixing)

Shelf life	1 year when stored in original, unopened packaging at 73°F (23°C)
Physical state	Powder and latex liquid

Application Properties (mixed neat)

Laboratory Tests	Results
Color of mixture	Dark gray
Mixing ratio (Part A : Part B = 8.9 : 1)	0.71 U.S. gal. (2,69 L) of <i>Mapecem 202</i> Part B latex liquid per 55-lb. bag (2,69 L per 24,9-kg bag) of <i>Mapecem 202</i> Part A powder
Consistency	Screed mortar
Density	131 lbs. per cu. ft. (2,10 kg per L)
pH (fresh mortar)	12.3
Slump – ASTM C143 (CAN/CSA-A23.2-5C)	9" (23 cm) (neat mortar)
Application temperature range	45°F to 95°F (7°C to 35°C)
Thickness per lift (neat)	1/4" to 2" (6 mm to 5 cm)
Pot life	30 minutes
Initial set – ASTM C191	60 minutes
Final set – ASTM C191	90 minutes
Open to traffic	4 hours

Mapecem 202



Application Properties (mixed with 20% of 3/8" [10 mm] pea gravel)*

Laboratory Tests	Results
Color of mixture	Dark gray
Compressive strength – ASTM C39 (4" x 8" [10 x 20 cm] cylinders)	
1 day	> 2,250 psi (15,5 MPa)
7 days	> 2,800 psi (19,3 MPa)
28 days	> 4,500 psi (31,0 MPa)

* See the chart titled "Application Properties (mixed neat)" for other mixture characteristics.

CSI Division Classifications

Cast in Place Concrete	033000
Cementitious Decks and Underlayment	035000
Concrete Restoration and Cleaning	039000

Packaging

Size	
Kit: 61.17-lb. (27,7-kg) kit	Bag, Part A powder: 55 lbs. (24,9 kg)
	Jug, Part B latex liquid: 0.71 U.S. gal. (2,69 L) and 6.17 lbs. (2,80 kg)

Approximate Yield** per 61.17-lb. (27,7-kg) kit (mixed neat)

0.47 cu. ft. (0,0133 m ³)

Approximate Coverage** per 61.17-lb. (27,7-kg) kit (mixed neat)

Thickness	Coverage
1/4" (6 mm)	23.4 sq. ft. (2,17 m ²)
1" (2,5 cm)	5.6 sq. ft. (0,52 m ²)
2" (5 cm)	2.8 sq. ft. (0,26 m ²)

** Coverage shown is for estimating purposes only. Actual jobsite coverage may vary according to substrate conditions and setting practices.

Refer to the SDS for specific data related to health and safety as well as product handling.

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in effect at the time of the MAPEI product installation. For the most up-to-date TDS and warranty information, please visit our website at

www.mapei.com. **ANY ALTERATIONS TO THE WORDING OR REQUIREMENTS CONTAINED IN OR DERIVED FROM THIS TDS SHALL VOID ALL RELATED MAPEI WARRANTIES.**

Before using, the user must determine the suitability of our products for the intended use,

and the user alone assumes all risks and liability. **ANY CLAIM SHALL BE DEEMED WAIVED UNLESS MADE IN WRITING TO US WITHIN FIFTEEN (15) DAYS FROM DATE IT WAS, OR REASONABLY SHOULD HAVE BEEN, DISCOVERED.**

We proudly support the following industry organizations:



TTMAC ACTM



aci
American Concrete Institute®

ASC
THE ADHESIVE AND SEALANT COUNCIL
SECURING THE FUTURE



MAPEI Headquarters of North America
1144 East Newport Center Drive
Deerfield Beach, Florida 33442
1-888-US-MAPEI (1-888-876-2734) /
(954) 246-8888

Technical Services
1-888-365-0614 (U.S. and Puerto Rico)
1-800-361-9309 (Canada)
Customer Service
1-800-42-MAPEI (1-800-426-2734)

Services in Mexico
0-1-800-MX-MAPEI (0-1-800-696-2734)
Edition Date: April 18, 2018
PR: 856 MKT: 17-2595

For the most current BEST-BACKED™ product data and warranty information, visit www.mapei.com.

All Rights Reserved. Printed in the USA. © 2018 MAPEI Corporation.